



Description	
Family	TARAFLEX SPORTS FLOORING
Product	MULTI-USE 3.0
Type	Roll
Style	Wood/Solid
Composition	100% first quality, pure vinyl, polyurethane PROTECSOL® Triple-Action.
Construction	Multilayered, calendered, printed design protected by a translucent pure vinyl wear layer injected with PROTECSOL®. Fibreglass grid. Supported by an expanded vinyl VHD (Very High Density) closed cell backing.
Reference specification	ASTM F 2772-09 Class I
Width	1.50 m (± 4'11")
Length	26.4 m (± 86'7")
Coverage	39.6 sq.m. (± 47.4 sq.yds.)
Thickness	3.0 mm (± .120")
Wear layer	1.4 mm (± .055")
Mid Ply	Fibreglass grid
Backing	Expanded vinyl ASTM F 2772-09 Class I
Weight	2.9 kg/sq.m. (± 5.3 lbs/sq.yd.)
Fiche technique	
Antibacterial	By properties of Sanosol®
Maintenance classification	✓✓✓ Best: ProtecSol®, treated, never wax
Coefficient of friction	EN 13036-4 / 80 TO 110
Static load	ASTM F 970-06 / 200 PSI (1379 kPa)
Electrostatic control	DIN 18032-2 ≥ 1000 N
Fire rating*	Canada - meets Canadian building code when tested in accordance with CAN/ULC S102.2-M88 USA - Class 1
Sound insulation	▲ L 16dB ASTM E 492-04 Impact Insulation Class (IIC) > 50
Abrasion	Superior wear resistant ASTM F 510-04
Ball Bounce	≥ 90%
Force reduction	≥ 16%
Energy return	≥ 0.31%
10 year limited warranty	Terms and conditions of the warranty are available on request.
Budget Pricing**	
Price per sq.ft. installed**	Consult your local distributor.

\* Flame spread rating as per ASTM E 648 - Critical Radiant Flux 0.45cm<sup>2</sup> or more (Class 1). As per ASTM E 662, (4 minutes, non flaming mode) - 450 or less. Other formulations can be made available on a special order basis. Call Gerflor for pricing, availability and minimum requirements. Numerical ratings do not necessarily constitute product performance under actual fire conditions. They are merely provided for product classification purposes.